

# AHB6057

## Face Material

weight	thickness	material
58±10g/m <sup>2</sup> ISO 536	0.04±10%mm GB/T6672	A gloss white laser PE+PET film for use in on-demand inkjet printers.

## Liner

83±10%g/m <sup>2</sup> ISO 536	0.8±10%mm ISO 534	white color kraft with PE coated, PEK release paper.
--------------------------------	-------------------	--

## Adhesive

It has excellent adhesion performance on non-polar surfaces. This is an adhesive with a high initial viscosity, which can be used for indirect to food, direct contact labeling of advertising stickers and cosmetics.

## Peel adhesion

initial adhesion 18 N/25mm FTM 9 st.st	20 minutes Peel adhesion value on steel at 180° 18N/25mm or tear off FTM 1 st.st	20 minutes Peel adhesion value on steel at 90° 9N/25mm or tear off FTM 2 st.st
---	--	--

## Temperature

Min. Appl. Temp. 5 °C	Service Temp. -35°C±65°C (24H after labeling)
-----------------------	---

## Applications

This product is an ideal choice for printing labels in on-demand-color inkjet printers, where full process color is used to add impact and/or functionality to the label.

The high ink holdout and quick drying provide for excellent clarity and density of printed graphics, making it the perfect choice for primary and secondary packaging labels in retail, manufacturing, health care, and logistics etc.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

## Conversion/printing

The product is designed to be converted and by all conventional converting technologies.

## Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23±2°C and 50±5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.