

# GAE7078

## Face Material

weight	thickness	material
80 ± 10%g/m <sup>2</sup> ISO 536	0.08 ± 10%mm ISO 534	Specially treated high gloss white coated paper

## Liner

weight	thickness	material
80 ± 10%g/m <sup>2</sup> ISO 536	0.083 ± 10%mm ISO 534	Single-color plastic-coated white CCK release paper

## Adhesive

A general permanent water-based acrylic adhesive. It is an adhesive with high initial viscosity and high final viscosity. It has excellent performance on many packaging materials. It can be used for information labels of food, books and periodicals, wine, beverages, electrical appliances and cultural goods.

## Peel adhesion

initial adhesion	20 minutes Peel adhesion value on steel at 180 angle	20 minutes Peel adhesion value on steel at 90angle
8 N/25mm or tear FTM 9 st.st	8 N/25mm or tear FTM 1 st.st	5 N/25mm or tear FTM 2 st.st

## Temperature

Min. Appl. Temp. 10 °C	Service Temp. -35°C ± 90°C (24H after labeling)
------------------------	---

## Applications

The surface material has good ink absorption performance and is widely used in the field of industrial and commercial labels, such as making wine labels and food labels.

The above suggestion, application, and elaboration are not intended as the guarantee of Jinya. All sales of Jinya products shall be tested by customer in the final environment to confirm compliance with the requirements of the use of environment.

## Printing Methods

High-gloss coated surface paper with high-gloss treatment, ideal for monochrome and color printing in a variety of printing processes. Attention should be paid to controlling the viscosity of the ink to prevent the coating from falling off due to the overly viscous ink. It is suitable for flat processing, and has good strength for die-cutting on flat or round equipment. Suitable for colorful graphic information printing. Avoid excessive rewinding tension, which will cause the adhesive to overflow. For fine barcode printing, a comprehensive print test evaluation is required. It can be printed on a roll, but the speed should not exceed 80m/S to avoid interruption and waste discharge.

### Shelf life

12 months, applicable only to the material delivered by Jinya which has not undergone further processing, under the following **STORAGE CONDITIONS**:

- This material must be stored at a temperature of 23 ± 2°C and 50 ± 5% of Relative Humidity.
- Storage area must be dry and clean.
- Keep the material in the original packaging when not used in order to protect it from dust and contamination.
- Do not expose to direct sunlight or heat sources.